



APPLIED TEXTILES LAB SERVICES  
**CERTIFICATE OF TESTING**

For The Account Of: **Bru Textiles**  
Satenrozen 2a  
B-2550 Kontich  
Belgium  
Contact: Tineke Verbruggen

DATE: February 11, 2008      CERTIFICATE (ORDER) NO.: 26224

CLIENT'S IDENTIFICATION: Calais

.....  
**TEST RESULTS**

**NFPA 701 - STANDARD METHODS OF FIRE TESTS FOR FLAME RESISTANT TEXTILES AND FILMS - 2004 EDITION - TEST #1**

The textile sample named above was tested and **PASSED** the NFPA 701 Test #1 - 2004.

Product Configuration:            ( x ) Single Layer            ( ) Multi Layer

Specimen #	<u>Initial Mass(g)</u>	<u>Final Mass(g)</u>	<u>% Weight Loss</u>	<u>Flaming Drip</u> <u>Seconds</u>	<u>Afterflame</u> <u>Seconds</u>
1	5.2	3.1	39%	0	0
2	5.2	3.1	41%	0	0
3	5.2	3.2	38%	0	0
4	5.2	3.1	40%	0	0
5	5.3	3.2	40%	0	0
6	5.3	3.1	41%	0	0
7	5.1	3.6	30%	0	0
8	5.1	3.3	35%	0	0
9	5.2	3.2	40%	0	0
10	5.2	3.3	37%	0	0
<b>Average</b>	<b>5.2</b>	<b>3.2</b>	<b>38%</b>	<b>0.0</b>	<b>0.0</b>

**Afterflame is required to be recorded; however, it is not factored into the Failure Criteria**

Approximate weight (oz./sq. yd): 2.495

SD = Standard Deviation            3 SD = Mean + 3 SD            g/m /(divided) x .835 = oz/yd

**PERFORMANCE CRITERIA:**

- Where fragments or residues of specimens that fall to the floor of the test chamber continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens, the material shall be recorded as failing. (Flaming Drip)
- Where the average weight loss of the 10 specimens in a sample is greater than 40 percent, the material shall be recorded as failing.
- Individual specimens will be listed as a failure if it exceeds mean + 3 SD
- Where the specimens do not demonstrate performance in accordance with either of the conditions indicated above, the material shall be recorded as passing this test and shall be designated as flame resistant.

**CONCLUSION:** Based on the above Results and Performance Criteria, the item tested:

  X   Passes             Fails             Testing of 10 additional specimens is required

**CERTIFICATION:** I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by the standards listed above.

Jennifer Friend - Lab Manager  
Applied Textiles Lab Services

Chavon McDaniel  
Lab Technician

A TEXTILE TESTING COMPANY  
555 76<sup>TH</sup> STREET SW, BYRON CENTER, MICHIGAN 49315  
TELEPHONE 616.559.6123 FACSIMILE 616.559.6119